



TRUPOTAN[®] US

masking basifying agent

Appearance:	beige powder
--------------------	--------------

Properties:

TRUPOTAN US is a safety basifying agent with well-balanced masking properties specially for un-split pelts.

A major advantage of **TRUPOTAN US** is the uniform and slow pH increase during basification. No risk of a sudden pH increase exists.

TRUPOTAN US provides a very even chrome distribution.

TRUPOTAN US improves chrome exhaustion and fixation.

TRUPOTAN US contributes to an excellent full and fine grain leather. The colour of the wet-blue is very clear and level.

Application:

TRUPOTAN US is added to the chrome liquor after the chrome has largely penetrated the pelt.

Due to the slow pH increase **TRUPOTAN US** can be added in one rate.

After addition of **TRUPOTAN US** the tanning process should be continued for approx. 9 hours so that a complete reaction can be guaranteed. The final temperature for the tanning process should be approx. 40 °C or higher (50 °C).

The usual quantity of **TRUPOTAN US** to be applied varies between 0.7 and 1.1 % (calculated on pelt weight) and depends upon thickness of the pelt, pickle pH-value and chromium offer.

Safety and storage:

It is recommended to wear a protective face mask when weighing.

The product should be stored in a dry place.

08/2004

The information given in this technical leaflet is offered in good faith and is based upon our knowledge and experience of the products used. The suitability of the products mentioned to obtain specific properties or effects are given without obligation or guarantee and should be fully tested by the end user and adapted to suit prevailing works conditions or other products which may be employed.

TRUPOTAN: registered trademark of TRUMPLER