



TRUPOTAN[®] RKM

polymer retanning agent

Basis:	polyacrylic acid compound
Appearance:	viscous liquid
Charge:	anionic
Active matter:	approx. 30 %
pH value (1 : 10):	approx. 7.5
Light fastness:	excellent
Heat yellowing:	excellent

Properties:

TRUPOTAN RKM is a polymer retanning agent on the basis of polyacrylic acids intended for the retannage of all types of leather.

TRUPOTAN RKM increases the fullness and grain tightness.

TRUPOTAN RKM eases the penetration of dyestuffs without reducing the dye intensity.

Application:

TRUPOTAN RKM can be applied in the neutralisation process or in the retannage. After neutralisation between 2 and 4 % **TRUPOTAN RKM**, based on shaved weight, can be used to increase the softness and fullness of the leather.

In the retannage between 2 and 6 % **TRUPOTAN RKM** can be applied, based on the shaved weight, to improve the grain tightness.

Safety and storage:

When handling **TRUPOTAN RKM**, normal safety precautions associated with the handling of chemicals should be observed. For more specific details please refer to our safety data sheets.

TRUPOTAN RKM can be stored for up to one year, if temperatures below 5 °C and above 40 °C can be avoided. On prolonged storage or extremes of temperature **TRUPOTAN RKM** may exhibit some settlement which can be rectified by either warming and/or stirring the product thoroughly before use.

06/2003

The information given in this technical leaflet is offered in good faith and is based upon our knowledge and experience of the products used. The suitability of the products mentioned to obtain specific properties or effects are given without obligation or guarantee and should be fully tested by the end user and adapted to suit prevailing works conditions or other products which may be employed.

TRUPOTAN: registered trademark of TRUMPLER