



TRUPOTAN[®] RP

polymer retanning agent

Basis:	polyacrylic acids
Appearance:	light viscous liquid
Charge:	anionic
Active matter:	approx. 30 %
pH value (1 : 10):	approx. 6
Light fastness:	excellent
Heat yellowing:	excellent

Properties:

TRUPOTAN RP is a polymer retanning agent based on acrylic acids for the retanning of all types of soft leathers.

TRUPOTAN RP increases the leather fullness.

TRUPOTAN RP produces leathers with a very good softness and a very fine grain.

TRUPOTAN RP produces low density light leathers and improves the milling properties.

TRUPOTAN RP has really excellent light fastness and heat fastness properties.

Application:

In the retanning between 3 and 6 % **TRUPOTAN RP**, based on shaved weight, is applied.

In the retannage of waterproof leathers between 3 and 6 % **TRUPOTAN RP** improves the fullness and the grain tightness without reducing the effect of the water resistant fatliquors for example **TRUPOSIST[®]**.

Safety and storage:

When handling **TRUPOTAN RP**, normal safety precautions associated with the handling of chemicals should be observed. For more specific details please refer to our safety data sheets.

TRUPOTAN RP can be stored for up to one year, if temperatures below 5 °C and above 40 °C can be avoided. On prolonged storage or extremes of temperature **TRUPOTAN RP** may exhibit some settlement which can be rectified by either warming and/or stirring the product thoroughly before use.

06/2003

The information given in this technical leaflet is offered in good faith and is based upon our knowledge and experience of the products used. The suitability of the products mentioned to obtain specific properties or effects are given without obligation or guarantee and should be fully tested by the end user and adapted to suit prevailing works conditions or other products which may be employed.

TRUPOTAN; TRUPOSIST: registered trademarks of TRUMPLER