



TRUPOTAN[®] VS

combination tanning agent

Basis:	diphenyl sulphone and phenolic compounds based on catechol tanning agents
Appearance:	light red brown powder
Charge:	anionic
Active matter:	approx. 94 %
pH value (1 : 10):	approx. 5

Properties:

TRUPOTAN VS is a combination tanning agent intended for the retanning of all types of leathers, but is especially suitable for the production of chrome-free upholstery leathers and car upholstery leathers.

With **TRUPOTAN VS** a well-filled, fine grained leather with a round handle is obtained.

TRUPOTAN VS brings about a dye levelling without reducing the colour value.

TRUPOTAN VS is very suitable for the production of leathers with low free formaldehyde content.

Application:

The quantity of **TRUPOTAN VS** to be applied will depend upon the type of leather required. When used in the tanning process of pre-tanned wet white, 15 - 20 % **TRUPOTAN VS**, based on shaved weight, will normally suffice to produce excellent fullness and handle. Application can be made in two additions at intervals of 60 mins.. If required, **TRUPOTAN GD** or **GDL** may be added in order to speed penetration and improve the colour.

When used in the retanning of wet blue, shoe or upholstery leather, quantities between 5 and 15 %, based upon shaved weight, will normally suffice to improve fullness and handle.

In order to avoid iron stains from contaminated water or shaving, it is recommendable to utilise small quantities of sequestering agent such as **RESISTOL[®] FE** in the process.

Safety and storage:

When handling **TRUPOTAN VS**, normal safety precautions associated with the handling of chemicals should be observed. For more specific details please refer to our safety data sheets.

The product should be stored in a dry, cool place.

08/2003

The information given in this technical leaflet is offered in good faith and is based upon our knowledge and experience of the products used. The suitability of the products mentioned to obtain specific properties or effects are given without obligation or guarantee and should be fully tested by the end user and adapted to suit prevailing works conditions or other products which may be employed.

TRUPOTAN, RESISTOL: registered trademarks of TRUMPLER