



# TRUPON<sup>®</sup> LC

fatliquor for shoe upper leather

<b>Basis:</b>	sulphated, animal and vegetable oils
<b>Appearance:</b>	pale coloured viscous oil
<b>Charge:</b>	anionic
<b>Active matter:</b>	approx. 78 %
<b>pH value (1 : 10):</b>	approx. 7.5
<b>Acid stability:</b>	low
<b>Salt stability:</b>	low
<b>Chrome stability:</b>	not recommended in chrome tanning
<b>Light fastness:</b>	good
<b>Heat yellowing:</b>	good

## Properties:

**TRUPON LC** is an anionic fatliquor designed for use on traditional shoe upper leathers which require a certain degree of „spring“ or „stand“.

**TRUPON LC** possesses only moderate stability to acid and salt and will, as a consequence, produce leathers with a slightly waxy handle which exhibit good glazing and burnishing properties.

**TRUPON LC** can be used to good effect in vegetable tanned leathers where its use will help to produce fine, flat grain characteristics.

## Application:

**TRUPON LC** can be used alone or in combination with other anionic fatliquors. We would not, however, recommend the addition of raw oils.

**Safety and storage:**

When handling **TRUPON LC**, normal safety precautions associated with the handling of chemicals should be observed. For more specific details please refer to our safety data sheets.

**TRUPON LC** can be stored for up to one year, if temperatures below 5 °C and above 40 °C can be avoided. On prolonged storage or extremes of temperature **TRUPON LC** may exhibit some settlement which can be rectified by either warming and/or stirring the product thoroughly before use.

04/2003

The information given in this technical leaflet is offered in good faith and is based upon our knowledge and experience of the products used. The suitability of the products mentioned to obtain specific properties or effects are given without obligation or guarantee and should be fully tested by the end user and adapted to suit prevailing works conditions or other products which may be employed.

TRUPON: registered trademark of TRUMPLER